

Technical Data Sheet

Norox[®] MEKP-925

DESCRIPTION

Norox[®] MEKP-925 has a high MEKP dimer content that gives excellent performance in most vinyl ester resins. Norox[®] MEKP-925 also performs well when used with general purpose ortho and isophthallic resins. Norox[®] MEKP-925 should be considered when an initiator is desired for use with most all resin types.

TYPICAL PROPERTIES

Active Oxygen:	9.0% max.
Form:	Liquid
Color:	Water white
Specific Gravity @ 25°/4°C:	1.10
Flash point (C.O.C):	200°F, min.
Flash point (SETA C.C.):	170°F, min.
Soluble in:	Oxygenated organic solvents
Slightly soluble in:	Water

APPLICATION

Norox[®] MEKP-925 is a methyl ethyl ketone peroxide composition formulated to be an excellent cure initiator for both unsaturated polyester resins and vinyl ester resins. With most unsaturated polyesters it gives longer gel and gel to cure times but with a higher peak exotherm than Norox[®] MEKP-9, particularly in thick sections.

PACKAGING, SHIPPING & AVAILABILITY

- The standard package sizes of Norox[®] MEKP-925 are cases of 4x8 lb. polyethylene bottles; and 40 lb. or 20 kg Hedpacks. For custom package sizes, please contact your local distributor or United Initiators SPI, Inc.
 - Classification – Please refer to the specific Norox[®] MEKP-925 Safety Data Sheet under section 14, Shipping Description.
 - Norox[®] MEKP-925 is available through a nation-wide distributor network. Call United Initiators SPI, Inc. for the name of the distributor in your area.
-
- **NOTE:** SDS's for all our products may be requested thru the website www.syrqispi.com

Disclaimer

This information and our application-technical advice – whether verbal, in writing or by way of trials – reflect our present state of knowledge based on internal tests with local raw materials. Their purpose is to inform interested parties about our products and their possible application. They should not be construed as guaranteeing specific product properties or their suitability for a particular application. Furthermore, the information does not contain complete instructions for use. Nor does it constitute a guarantee as to quality and durability. Changes due to technical progress and corporate advancement reserved. Any existing third-party copyrights are to be taken into account.

Application and use of our products based on our application-specific advice is beyond our control and sole responsibility of the user. The user is not released from the obligation of verifying the suitability and applicability as to the intended purpose.